

Dress up your Luxury Project

Prodotti per Legatoria - Cartotecnica - Arti Grafiche
Saldatori Plastici Campionaristi Scatolifici

Registered Office: 20138 Milan - Via M.F. Quintiliano, 2/4
Administrative Offices: 20138 Milan - Via Salomone, 43
T. +39 (02) 58.012.660 - 58.011.069 F. +39 (02) 50.633.14
Share Capital € 100.000 i.v. - REA MI 1252539
VAT No. 08837680159

www.cavalliniring.it - vendite@cavalliniring.it
Certified Email PEC: cavallinisrl@ticertifica.it

"Since 1987... Quality & Service"

DAINEL COLLECTION

As the exclusive distributor of this flocked covering material in Italy, Cavallini S.r.l. supplies this product exclusively within the Italian market.

AVAILABLE BACKINGS

SG: 95 g/m² paper backing
PVC: 250 µm plastisol backing
Board: 300 g/m² paperboard backing
CC: 400 g/m² paperboard backing
AC29: Acrylic adhesive backing

TECHNICAL SPECIFICATIONS - DAINEL SG

Total Grammage: 230 ± 25 g/m²
Average Thickness: 0,50 ± 0,05 mm
Residual pH: ≥ 8
Light Fastness (Blue Wool Scale): 4 to 7 depending on colour
Loose Flock Fibres: ≤ 0,3 g/m²
Roll Size: 100 mt x 104 cm
Roll Weight: 27 kg Except Neige, supplied in 50 m rolls.

TECHNICAL SPECIFICATIONS - DAINEL PVC

Grammage: 470 ± 25 g/m²
Thickness: 0,60 ± 0,05 mm
Light Fastness (Blue Wool Scale): 4 to 7 depending on colour
Loose Flock Fibres: ≤ 0,3 g/m²
Roll Size: 140cmx50 mt
Roll Weight: 35 kg Except Neige, supplied in 40 m rolls.

TECHNICAL SPECIFICATIONS - DAINEL BOARD

Grammage: 440 g/m²
Sheet Size: 70x100 cm

TECHNICAL SPECIFICATIONS - DAINEL CC

Grammage: 540 g/m²
Sheet Size: 70x100 cm

TECHNICAL SPECIFICATIONS - DAINEL AC29

Grammage: 375 g/m²
Thickness: 0,65 ± 0,05 mm
Light Fastness (Blue Wool Scale): 4 to 7 depending on colour
Loose Flock Fibres: ≤ 0,3 g/m²
Roll Size: 10 mtx50 cm
Roll Weight: 2,5 kg



Discover our FSC® certified products

Only the products that are identified as such on this document are FSC® certified

USAGE INFORMATION

It is recommended that the material be used within one year of delivery. AC29 adhesive-backed material should be stored at a temperature between 20°C and 25°C.

GENERAL HOT FOIL STAMPING CONDITIONS

0,5 sec – temperature 120 °C – pressure approximately 200 kg/cm²

For further recommendations on hot foil stamping, please refer to HC and AS foils available at (www.kurz.de)

ADDITIONAL INFORMATION

Neutral product (does not damage precious metals).

Free from azo compounds and asbestos.

Free from volatile organic compounds (VOCs).

DAINEL SG complies with EN 71-3 (Safety of Toys – Part 3).

Specific colour tolerances apply to each colour.



Discover our FSC® certified products

Only the products that are identified as such on this document are FSC® certified